

Sub A

at least one conductive layer between the aluminum oxide layer and the substrate,

10

15

20

25

5. The magnetic recording medium according to claim 1, wherein the conductive layer includes Cu as a

**SECRET**

component.

5 6. The magnetic recording medium according to claim 1, wherein a portion of each of the fillers with which the holes are filled, the portion which contacts the conductive layer, has fcc structure and its (111) face is oriented in a direction perpendicular to the substrate.

10 7. The magnetic recording medium according to claim 6, wherein the portion touching the conductive layer includes Cu as a component.

15 8. The magnetic recording medium according to claim 6, wherein the portion touching the conductive layer includes NiFe as a component.

20 9. The magnetic recording medium according to claim 2, wherein the hard magnetic substance including Co includes at least one element among Cu, Cr, P, Ni, Pt, and Pd.

25 10. The magnetic recording medium according to claim 1, wherein materials from the conductive layer to the hard magnetic substance are given epitaxial growth.

11. The magnetic recording medium according to

09964781.092804  
108260-18249560

claim 1, wherein a soft magnetic substance layer is formed under the conductive layer.

12. The magnetic recording medium according to claim 1, wherein the holes are arranged in a honeycomb array.

13. The magnetic recording medium according to claim 1, wherein the holes are arranged in a rectangular array.

~~14. A magnetic record and reproduction apparatus using the magnetic recording medium according to claim 1.~~

15. A magnetic recording medium, in which an aluminum oxide layer having holes on a substrate is filled with a magnetic substance, comprising:

at least one conductive layer between the aluminum oxide layer and the substrate,

wherein the conductive layer has fcc structure and its (001) face is oriented in a direction perpendicular to the substrate, and the magnetic substance includes a hard magnetic substance that has  $L1_0$  structure and the c-axes of which are oriented in the direction perpendicular to the substrate.

I. As claims 15-35

amendable

II. D

claim 6 amendable

5

10

15

20

25

21. The magnetic recording medium according to claim 16, wherein materials from the conductive layer to the hard magnetic substance including MPt (M = Co,

Fe, Ni) are given epitaxial growth.

22. The magnetic recording medium according to claim 15, wherein an MgO (001) layer is formed under the conductive layer.

23. The magnetic recording medium according to claim 15, wherein a soft magnetic substance layer is formed under the conductive layer.

24. The magnetic recording medium according to claim 15, wherein the holes are arranged in a honeycomb array.

15            25. The magnetic recording medium according to  
claim 15, wherein the holes are arranged in a  
rectangular array.

~~26. A magnetic record and reproduction apparatus using the magnetic recording medium according to claim 15.~~

27. A magnetic recording medium, in which an aluminum oxide layer having holes on a substrate is filled with a magnetic substance, comprising:

25           at least one conductive layer between the aluminum  
oxide layer and the substrate, wherein the conductive  
layer has any one of  $L1_0$ ,  $L1_1$ , and  $L1_2$  ordered

Sub A (20)

structures, and its square array face is oriented in a direction perpendicular to the substrate, and the magnetic substance includes a hard magnetic substance that has the  $L1_0$  structure and the c-axes of which are oriented in the direction perpendicular to the substrate.

28. The magnetic recording medium according to claim 27, wherein the hard magnetic substance includes MPt (M = Co, Fe, Ni).

29. The magnetic recording medium according to claim 28, wherein the conductive layer has any one among  $L1_0$  ordered structure including MPt (M = Co, Fe, Ni),  $L1_1$  ordered structure including CuPt, and  $L1_2$  ordered structure including  $CoPt_3$ .

30. The magnetic recording medium according to claim 28, wherein the hard magnetic substance including MPt (M = Co, Fe, Ni) includes at least one element among Cu, Cr, P, Ag, and Pd.

31. The magnetic recording medium according to claim 28, wherein materials from the conductive layer to the hard magnetic substance including MPt (M = Co, Fe, Ni) are given epitaxial growth.

32. The magnetic recording medium according to claim 27, wherein an MgO (001) layer is formed under the conductive layer.

5 33. The magnetic recording medium according to claim 27, wherein a soft magnetic substance layer is formed under the conductive layer.

10 34. The magnetic recording medium according to claim 27, wherein the holes are arranged in a honeycomb array.

15 35. The magnetic recording medium according to claim 27, wherein the holes are arranged in a rectangular array.

20 ~~36. A magnetic record and reproduction apparatus using the magnetic recording medium according to claim 27.~~

25 ~~37. A method of manufacturing a magnetic recording medium that has a film with anodic oxidized alumina nanoholes filled with a magnetic substance, comprising:~~

~~a step of preparing a substrate;~~

~~a step of forming a conductive layer, which has fcc structure and its (111) face is oriented in a~~

10964781 003001

Sub  
APC

40. A method of manufacturing a magnetic



5

a step of forming a conductive layer, which has fcc structure and whose (001) face is oriented in a direction perpendicular to the substrate, and an aluminum layer on the substrate;

10

a step of formation of hard magnetic substance oriented the c-axes in a direction perpendicular to the substrate in  $L1_0$  ordered structure by annealing process.

20

a step of forming a conductive layer, which has any one of  $Ll_0$ ,  $Ll_1$ , and  $Ll_2$  ordered structure, and a square lattice face of which is oriented in a direction perpendicular to the substrate, and an aluminum layer on the substrate;

a step of anodizing the aluminum layer and forming

a step of electrodepositing a layer including MPt (M = Co, Fe, Ni) in each of the alumina nanoholes; and

a step of formation of hard magnetic substance

42. The method of manufacturing a magnetic recording medium according to claim 40, further

comprising a step of electrodepositing a nonmagnetic layer, which has fcc structure including any one among Pt, Pd, Cu, Ir, and Rh, and whose (001) face is oriented in a direction perpendicular to the substrate, before the step of electrodepositing the layer

43. The method of manufacturing a magnetic recording medium according to claim 41, further

comprising a step of electrodepositing a soft magnet  
layer, which has fcc structure mainly including NiFe  
and whose (001) face is oriented in a direction

perpendicular to the substrate, before the step of electrodepositing the layer including MPt (M = Co,